

SECTION 724 PAVEMENT PATCHING, WIDENING AND JOINT REPAIR

MATERIAL		REFERENCE	PURP.	SAMPLED BY	MIN. FREQ.	MIN. QUANT.	CERT.	SMALL QUANTITY	TYPICAL HANDLING TIME	REMARKS
		TESTED BY		METHOD		CONTAINER	DISTR.			
ASPHALTIC CONCRETE		FOR DETAILS ON ADDITIVES, AGGREGATES, ASPHALT CEMENTS, ASPHALTIC CONCRETE, ASPHALTIC TACK COAT, ASPHALT MIX RELEASE AGENT AND MINERAL FILLER, SEE SECTION 501 OF THIS MANUAL.						-----	-----	Roadway density requirements for patching and widening are 1 per 100 tons or maximum of 5 per lot from the top 4 inches of finished section.
CONCRETE-PORTLAND CEMENT (Pavement and Structural)	Class A	FOR DETAILS OF CONCRETE AND ASSOCIATED MATERIALS, SEE SECTIONS 601 AND 901 OF THIS MANUAL.						-----	-----	-----
	Compressive Strength	601.18(b)(2) 724.08(a)(1) Dist. Lab	Accept.	Proj. Engr. S 301	3 cyl/batch 2 batches/lot	1 ft ³ 6 in. x 12 in. cylinder mold	----	-----	30 days	A lot is a complete section or an identifiable pour that is completed in one day.
GRANULAR MATERIAL		724.02 1003.07 Dist. Lab	Accept.	Proj. Engr. S 101	1/1000 yd ³	1 full sample sack	-----	-----	4 days	-----