

Method of Test For
DETERMINATION OF THE COMPACTION FACTOR OF BASE MATERIAL
DOTD DESIGNATION: TR 419

I. Scope

- A. This method of test is intended for determining the ratio of the loss in volume due to compaction.

II. Procedure

- A. Determine the average of the loose and dense unit weights in accordance with DOTD Designation TR-417.
- B. Compute the dry weight of the average unit weight found in step (A).
- C. Determine the maximum dry density in accordance with DOTD Designation TR-418.
- D. Compute the compaction factor: Divide the maximum dry density, Step (C), by the dry weight of the average mixture found in step (B).

III. Calculations

Compaction factor = $\frac{\text{Maximum Dry Density}}{\text{Dry weight of mixture}}$

$$\text{Compaction factor} = \frac{138.0}{101.5} = 1.36$$

Normal testing time is 3days.